

## JOUBERT POPLY



Poplar throughout - Face veneers II/III  
Gluing class 2 or class 3 - E1

Light colour and light material.

Interior layout.

Wall facings, manufacture of furniture, packing cases.

### TECHNICAL INFORMATION

#### GENERAL INFORMATION

Compliance of plywood with European norms:

- Gluing class: according to EN 314-2
- Faces classification: according to EN 635-2
- Dimension tolerance: according to EN 315
- Panel marking: according to EN 636
- Use class 2: according to EN 335

#### SPECIFICATIONS

Thicknesses: 4 to 30 mm.

**CE 2+** marking for structural use (according to EN 13986) for panels with a thickness  $\geq 8$  mm (control certificate delivered by FCBA).

**CE NS** marking for non-structural use (according to EN 13986) for panels with a thickness  $< 8$  mm or gluing class 3.

Density:	450 kg/m <sup>3</sup> ( $\pm 50$ kg/m <sup>3</sup> )
Fire reaction:	D-s2, d0 for thicknesses $\geq 9$ mm* E for thicknesses $< 9$ mm*
Formaldehyde emission:	Class E1 US EPA TSCA Title VI - CARB ULEF
Heat conductivity:	$\lambda = 0,11$ W/m.k
Pentachlorophenol content:	$< 5$ ppm

\* Depending on how the panel is installed.



Thickness mm	Sizes cm
4	<b>GLUING CLASS 2</b>
5	250 x 122
6	252 x 185
8	310 x 153
9	
10	<b>GLUING CLASS 3</b>
12	250 x 122
15	252 x 185
18	310 x 153
20	
22	
25	
30	

For PEFC-certified panels, depending on available credits, contact us.